



NEVASTANE MP 1.5

DESCRIPTION

Extreme pressure and water-resistant calcium complex grease for food industry.



No MOAH (Mineral Oil Aromatic Hydrocarbons).

***The Nevastane range will not contribute to MOAH content in foods when used in accordance with FDA 21CFR178.3570 limitations.**

SPECIFICATIONS

- **NEVASTANE MP 1.5** is formulated in accordance with US FDA Regulation 21 CFR, 178.3570.
- **NEVASTANE MP 1.5** is **NSF H1** registered: No 156333 and ISO 21469 certified.
- ISO 6743-9 : L-XBDFB 1/2
- DIN 51 502 : KP1/2N-20

APPLICATIONS

- **NEVASTANE MP 1.5** is specially developed for lubricating manufacturing or packaging machines used in the food industry, such as grape harvesters and pellet presses.
- **NEVASTANE MP 1.5** is suitable for lubricating loaded or unloaded mechanical devices such as bearings, joints, reducers, slides, cam systems, sealing devices and various transmissions.

ADVANTAGES

- **NEVASTANE MP 1.5** extends the equipment life while reducing contamination problems as required by the Hazard Analysis and Critical Control Point System (HACCP).
- Excellent water washout resistance and protection against corrosion.
- Simplification of the lubrication process

This lubricant used as recommended and for the application for which it has been designed does not present any particular risk.
A material safety data sheet conforming to the regulations in use in the E.C. can be obtained from your local commercial adviser or down loaded at ms-sds.totalenergies.com

RECOMMENDATIONS

- Store the product at temperatures between 0 and 40°C.
- Shelf life: 2 years from date of manufacture (unopened).
- Always avoid contamination of the grease by dust and/or dirt when applying

TYPICAL CHARACTERISTICS

TYPICAL CHARACTERISTICS	METHODS	UNITS	NEVASTANE MP 1.5
Soap/thickener	-	-	Calcium Complex
Color	Visual	-	White
Appearance	Visual	-	Smooth
NLGI grade	ASTM D 217	grade	1.5
Operating temperature range	-	°C	from -20 to 150
Penetration at 25 °C	ASTM D 217	0.1 mm	295-335
Four ball weld load	ASTM D 2596	kgf	>315
Water washout 1h@80°C - weight loss	ASTM D 1264	% wt	<10
Dropping point	IP 396	°C	> 300
Base oil			White oil
Kinematic viscosity of the base oil at 40 °C	ISO 3104	mm ² /s	150

Above characteristics are mean values given as an information.

This lubricant used as recommended and for the application for which it has been designed does not present any particular risk.
A material safety data sheet conforming to the regulations in use in the E.C. can be obtained from your local commercial adviser or down loaded at ms-sds.totalenergies.com