



MULTIPLEX S2A

APPLICATIONS

Multi purpose medium duty
EP grease
General lubrication
Centralized lubricating
system

Recommendation

- **MULTIPLEX S2 A** is a semi synthetic lithium complex grease designed for the lubrication various application in all types of operating conditions, but particularly where the operation temperature is high and the use of conventional lithium greases is limited.
- **MULTIPLEX S2 A** is a true multi purpose grease, formulated for lubrication of loaded slide-, ball- and roller-bearings, wheelbearings, universal joints, chassis, and various shock loaded or vibrating applications in transport, agriculture and off road vehicles.
- **MULTIPLEX S2 A** is suitable as general purpose grease for industrial applications requiring a NLGI 2 grade Extreme Pressure grease, resistant to elevated temperatures..
- Always avoid contamination of the grease by dust and/or dirt when applying. Preferably use a pneumatic pump system or cartridges.

SPECIFICATIONS

- ISO 6743-9 : L-XBEHB 2
- DIN 51502 : KP2P- 25

ADVANTAGES

Extensive application
range
Durable film
Mechanical stability
Thermal stability

Miscible
No harmful substances

- Thanks to its sophisticated formulation MULTIPLEX S2 A meets a wide variety of requirements.
- Its range of application is extensive, allowing stock rationalization and simplification of maintenance.
- Fulfills the requirements of most automotive Original Equipment Manufacturers.
- Miscible with most other conventional soap greases.
- Forms a lubricating film which is durable, and resistant to humidity, temperature variations and pollution, and hence reduces maintenance and costs.
- **MULTIPLEX S2 A** does not contain lead, or other heavy metals considered harmful to human health and the environment.

CHARACTERISTICS

TYPICAL CHARACTERISTICS	METHODS	UNITS	MULTIPLEX S2 A
Soap/thickener		-	Lithium complex
NLGI grade	ASTM D 217/DIN 51 818	-	2
Color	Visual	-	Blue
Appearance	Visual	-	Smooth
Operating temperature range		°C	- 25 to 160
Penetration at 25°C	ASTM D 217/DIN51 818	0.1 mm	265 - 295
Four ball weld load	DIN 51 350-4	daN	280 - 300
Anti-rust performance SKF- EMCOR	DIN 51 802/IP220/NFT 60-135/ISO 11007	rating	0 - 0
Dropping point	IP 396/DIN ISO 2176	°C	> 250
Viscosity of the base oil at 40°C	ASTM D 445/DIN 51 562-1/ISO 3104/IP71	mm ² /s (cSt)	120

Above characteristics are mean values given as an information.